

Technical Bulletin # 812F

Product Description

IMPAX 33 Primer is a low viscosity, 100% solids, high build, fast cure epoxy primer designed for use under IMPAX 650SL and IMPAX 650HB or where a high build primer is needed. This primer/seal coat enhances adhesion by penetrating into the concrete substrate and helps reduce bubbling and pinholes that may occur when coating porous surfaces with high build coatings. IMPAX 33 meets OSHA, State VOC regulations and USDA standards for maintenance protective coatings not in direct contact with food in federally inspected meat and poultry plants.

Use & Benefits

IMPAX 33 is intended as a high build primer for use on open or porous substrates where it is necessary to cover a rough surface profile with a pigmented topcoat. Concrete substrates that are scarified, shotblasted or sandblasted may have a coarse profile requiring a primer that both penetrates and seals the surface.

Surface Preparations

New Concrete: All surfaces must be firm, clean, dry and well cured before coating. Newly poured concrete must age at least 30 days at temperatures over 70°F before coating. Form release agents, curing compounds, salts, hardeners and other foreign matter will interfere with adhesion and must be removed by sandblasting, shotblasting, mechanical scarification or suitable chemical means. If a curing membrane was not used, then proceed with a 16% muriatic acid (1 gal. 32% muriatic acid to 1 gal. water) at a rate of 75 sq. ft./gal.

Old Concrete: Coating older, uncoated concrete floors is done in much the same manner as new concrete. Before etching, the concrete surface must be thoroughly cleaned with a strong detergent cleaner to remove all grease, oils, etc. All loose concrete must be removed. Form release agents, hardeners, etc., must be removed using same procedure as for new concrete. Holes and cracks should be filled with ITW REPAIR COMPOUND before application of a coating. If surface deterioration presents an unacceptably rough floor, IMPAX 5020 Floor Resurfacer is recommended to patch and resurface damaged concrete.

Wood: A clean, sound wood surface is required. Remove any oils and dirt from the surface using degreasing solvent or strong detergent. Follow with sanding to remove loose or deteriorated surface wood and to obtain the proper surface profile.

Mixing and Application Instructions

Before mixing IMPAX 33 it is important that the surface is completely prepared and ready and that all tools and equipment are handy. To mix 1 gallon units: Use electric or air mixer (approximately 250 rpm) with metal mixing blade (Jiffy Model HS or equal). Pour hardener contents into slack-filled resin can and mix for 2 to 3 minutes until material is thoroughly blended. To mix 5 gallon units: Use same procedure as 1 gallon units except a larger blade (Jiffy Model ES or equal) is required.

Immediately pour a substantial portion of mixture onto the floor and spread material using a flat, rubber squeegee using sufficient pressure to work the primer into the porous surface. Immediately backroll the material with a quality 3/8" nap roller leaving 6 to 10 mils on the surface.

The fast set primer can be top-coated in 6 hours at 72°F (22°C). The primer must be tack free before top-coating. If pinholes or porosities are evident after initial cure of the primer, re-priming may be necessary; especially on very porous concrete.

Precautions

Maintain good ventilation and avoid breathing vapors. Avoid prolonged and repeated skin contact. Wear safety glasses and impervious gloves.

ITW POLYMER TECHNOLOGIES

130 Commerce Drive • Montgomeryville, PA 18936 • 215-855-8450 • Fax 215-855-4688
www.chockfastgrout.com • www.escoweld.comITW Polymer Technologies
Registered to ISO 9001:2008
File No. A5798ITW Performance Polymer Europe
ISO 9001:2008
Q 06420

Physical Properties

VOLUME SOLIDS	100%
VOC (Based on mixed components)	0 lbs./gal. (0 gms./ltr.) (Based on mixed components)
FLASH POINT	200°F (93°C)
VISCOSITY	800 cps
SERVICE TEMPERATURE	180°F (82°C) Dry Heat Resistance

Product Information

COLOR	Light Gray
GLOSS	Satin Sheen
COVERAGE	200 sq. ft./gal. @ 8 mils DFT/WFT (4.9 m ² /liter @ 200 microns WFT/DFT)
APPLICATION TEMPERATURE	55°F minimum to 95°F maximum (12°C minimum to 35°C maximum) *Must be 5°F above dew point
RECOAT	Minimum - 6 Hours @ 72°F (22°C) @ 50% RH Maximum - 24 Hours @ 72°F (22°C) @ 50% RH
MIXING RATIO	2.2 to 1 parts epoxy resin/hardener by volume
INDUCTION	None
RELATIVE HUMIDITY	85% maximum
POT LIFE	30 Minutes @ 72°F (22°C)
CURE TIME (approximate)	Fully cured in 7 days
REDUCER	Not recommended
CLEAN UP	IMPAX IXT-59 Solvent
SHIPPING WEIGHT	
PACKAGING per Unit	1 gal. unit containing 1 gal. can (slack-filled) resin, ½ gal. Can (slack filled) hardener (3.7 liters unit volume) 5 gal. unit containing 5 gal. can (slack-filled) resin, 1½ gal. plastic jug hardener (18 liters unit volume)
SHELF LIFE	18 months in closed container stored @ 50°F to 90°F (10°C to 32°C)

Reference

For more detailed information on surface preparation please request Bulletin No. 994 or contact ITW Polymer Technologies' Engineering Services Department.

Date

09/2005

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support.

Warranty: ITW Polymer Technologies, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment.

Warranty Claims: If any product fails to meet the above, ITW Polymer Technologies will, at its option, either replace the product or refund the purchase price. ITW Polymer Technologies will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered.

Disclaimer: ITW Polymer Technologies makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose.

Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Polymer Technologies' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Polymer Technologies' election. Under no circumstances shall ITW Polymer Technologies be liable for any indirect, incidental or consequential damages.

Modification of Warranty: No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Polymer Technologies. No term of any purchase order shall serve to modify any provision of this document.

Mediation and Arbitration: If any dispute arises relating to products or product warranties, either the purchaser or ITW Polymer Technologies may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.